

IN THE CLAIMS

This listing of claims replaces all prior listings.

1. (previously presented) A method for manufacturing a micromachine including an oscillator, comprising:
 - a step of forming a sacrifice layer around a movable portion of the oscillator, the sacrificial layer comprising silicon dioxide;
 - a step of covering the sacrifice layer with an overcoat film, followed by the formation of a penetrating hole reaching the sacrifice layer in the overcoat layer;
 - a step of performing sacrifice-layer etching for removing the sacrifice layer using the penetrating hole in order to form a space around the movable portion; and
 - a step of performing a film-formation treatment at a reduced pressure following the sacrifice-layer etching so as to seal the penetrating hole, the film-formation treatment forming a film selected from the group consisting of an aluminum copper film and an aluminum silicon film.
2. (original) The method for manufacturing a micromachine, according to claim 1, wherein the method is applied to a micromachine having means for driving oscillation in the oscillator.
3. (original) The method for manufacturing a micromachine, according to claim 2, wherein static electricity is used as the means for driving oscillation.
4. (original) The method for manufacturing a micromachine, according to claim 2, wherein piezoelectricity is used as the means for driving oscillation.
5. (original) The method for manufacturing a micromachine, according to claim 1, wherein the film-formation treatment at a reduced pressure is a film-formation treatment by sputtering.